(1) Publication number:

0 121 929

А3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 84103966.2

(22) Date of filing: 09.04.84

(5) Int. Cl.4: **B 22 C 9/06** B 29 C 1/00, B 28 B 1/26

(30) Priority: 09.04.83 JP 62784/83

22.04.83 JP 71259/83 11.05.83 JP 80943/83 10.02.84 JP 23856/83

(43) Date of publication of application: 17.10.84 Bulletin 84/42

(88) Date of deferred publication of search report: 20.05.87

(84) Designated Contracting States: AT BE CH DE FR GB IT LI LU NL SE

(71) Applicant: SINTO KOGIO, LTD. No. 7-23, Meieki 4-chome Nakamura-ku Nagoya-shi Aichi-ken(JP)

(72) inventor: Yanagisawa, Akira No. 481-1, Aza-Nishihara Miyashiro-machi Minami-Saitama-gun Saitama-ken(JP)

(72) Inventor: Noguchi, Hiroyuki No. 34-2-1009, Senjumotomachi Adachi-ku Tokyo(JP)

(72) Inventor: Nakagawa, Takeo No. 223-4, Ichinotsubo Nakahara-ku, Kawasaki-shi Kanagawa-ken(JP)

(72) Inventor: Inagaki, Takehiro No. 122, Suwa-machi, 3-chome Toyokawa-shi Aichi-ken(JP)

(72) Inventor: Hayashi, Yoshikazu Dai-2 Kyowa-sou Mansion 403 No.32-117-chome, Toyosato Higashiyodogawa-ku Osaka-shi, Osaka(JP)


(72) Inventor: Tsuchida, Masanobu No. 80, Aza-Nashikogi, 9-chome Motojuku-machi Okazaki-shi, Aichi-ken(JP)

(72) Inventor: Fuma, Toyoji No. 57-1, Chubu-machi 2-chome, Toyokawa-shi Aichi-ken(JP)

(74) Representative: Heusler, Wolfgang, Dipl.-Ing. et al, Von Bezold, Dieter, Dr. Schütz, Peter, Dipl.-Ing. Heusler, Wolfgang, Dipl.-Ing. Maria-Theresia-Strasse 22 Postfach 860 260 D-8000 München 86(DE)

(54) Permeable mold.

(57) A durable and permeable mold for liquid, slurry, soft, sheet or lump materials is made up of a composite sintered body (1) comprising aggregates of ferrous or non-ferrous metallic grains and ceramic grains, to which a binder contained in evaporating or consumable substance is added. The body (1) has a close hardened surface region or layer (2) in which metallic oxides are scattered. The hardened layer (2) has fine air vents (22) in its thickness. The whole body (1) of the mold has a porosity of 5 to 60% and compression strength of more than 100 kg/cm2.







EP 84 10 3966

	DOCUMENTS CON	SIDERED TO	BE RELEVAN	T	Page 2
ategory	Citation of document with indication, where appropriate, of relevant passages			Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
A	US-A-4 425 411 al.) * Abstract *	(M. TEXT	OR et	1	
]					
					TECHNICAL FIELDS SEARCHED (Int. Cl. ?)
	The present search report has b	een drawn up for all	claims		
Place of search THE HAGUE Date of complete 11-02-			etion of the search	Done	Examiner GAS K.P.R.
docu	CATEGORY OF CITED DOCL cularly relevant if taken alone cularly relevant if combined w ment of the same category nological background written disclosure		E: earlier pate after the fill D: document	ent document, b	ring the invention ut published on, or lication easons



EUROPEAN SEARCH REPORT

84 10 3966 EP

	DOCUMENTS CONS					
Category	Citation of document w of rele	ith indication, where appropri vant passages	iate,	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Ci. 3)	
х	BE-A- 628 328 GmbH) * Page 2, lin 2,4,6,8; page 5	es 29-34; c		1,5-6	B 22 C 9/06 B 29 C 1/00 B 28 B 1/26	
Y	* claims 2,4,6,	8 *		3-4,9 12,14	•	
Y	CH-A- 617 914 * Page 2, coluclaim 1; page 3 19-24 *	mn 2, lines 5) 0-53; lines	3-4		
Y ·	US-A-4 125 351 al.) * Claim 1 *	 (F. ALFTER e	t	12	:	
	" Claim 1 "				TECHNICAL FIELDS SEARCHED (Int. CI 3)	
Y	FR-A-2 457 753 * Page 1, lines	(INVENTA AG) 8-13; claim	1 *	9	B 22 C B 28 B B 29 C	
Y	US-A-2 841 823 HARTESVELDT) * Column 1, lin			10-11	C 03 B	
Y	US-A-4 307 867 * Claim 1 *	 (R.F. SHANNOI	N)	14		
	-	/-	-			
	The present search report has b					
Place of search THE HAGUE Date of completion 11-02-1				Dong	Examiner LAS K.P.R.	
CATEGORY OF CITED DOCUMENTS X						